



HEMPEL'S THINNERS 08...

HEMPEL PAINT is produced and supplied in such a way that thinning is normally not necessary provided the paint is properly mixed/stirred.

However, if the paint is to be applied in a low film thickness (for instance as a "sealer coat") or if the paint has become too thick, e.g. in cold weather, the HEMPEL THINNER(s) indicated on the product data sheet may be added to obtain a consistency most suitable for application. As a general rule, thinning should be kept at a minimum as the quality of the paint work will suffer from too liberal thinning. However, if application is to take place at high temperatures (air and/or steel), thinning may even beyond the limits mentioned on the data sheets exceptionally be necessary in order to avoid dry-spray and poor film formation.

HEMPEL'S THINNERS are blended to give the best results with regard to brush ability, spray properties, etc.

In some cases ordinary solvents may substitute. As such products are beyond our control, we disclaim any responsibility for the results.

In each case the respective product data sheet and - when available - the APPLICATION INSTRUCTIONS should be consulted. As regards the use of THINNERS for cleaning of tools, see REMARKS overleaf.

HEMPEL'S THINNER NO.	FLASH POINT	EXAMPLES OF GENERAL USE
08080	25°C/77°F	HEMPEL'S ANTIFOULINGS: BLAKES TIGER XTRA 71000, BLAKES CRUISING 7100N, HEMPEL'S MILLE XTRA 71100, HEMPEL'S MILLE ULTIMATE 2 71102, BLAKES OCEAN PERFORMER 7110E, HEMPEL'S GLIDE CRUISE 7110G, HEMPEL'S MILLE PERFORMER 7110H, HEMPEL'S MILLE WHITE 71150, HEMPEL'S ALUSAFE 7120D, HEMPEL'S ALUXTRA 71260, HEMPEL'S RACING LIGHT 71350, HEMPEL'S MILLE LIGHT 71400, HEMPEL'S HARD RACING XTRA 71420, HEMPEL'S GLIDE SPEED 7142G, BLAKES HARD RACING 7142H, BLAKE'S GLIDE SPEED 7142T, HEMPEL'S MILLE WHITE SE 71600, HEMPEL'S MILLE ULTIMATE 71702, HEMPEL'S MILLE DYNAMIC 71704, HEMPEL'S GLIDE CRUISE 7170G, HEMPEL'S BASIC 76111, HEMPEL'S HARD RACING WHITE 76300, HEMPEL'S GLIDE SPEED WHITE 7630D, HEMPEL'S HARD RACING 76484, HEMPEL'S GLIDE SPEED 7648G, HEMPEL'S SEATECH ANTIFOULING 7820D.
08230	32°C/90°F	Brush thinner where THINNER 08080 is specified as spray thinner only. Thinner for one-pack varnishes. HEMPEL'S PRIMER UNDERCOAT 13201, HEMPEL'S UNDERWATER PRIMER 26030, HEMPEL'S MULTICOAT 51120
08450	23°C/73°F	HEMPEL'S LIGHT PRIMER 45551. Cleaning of tools used for HEMPEL'S EPOXY ADHESIVE 05674, HEMPADUR SEALER 599 and for HEMPEL'S HIGH PROTECT 35651
08510	3°C/37°F HIGHLY FLAMMABLE	Spray thinner for HEMPEL'S POLY BEST 55551
08710	47°C/116°F	Brush thinner for HEMPEL'S DIAMOND VARNISH 05140 and HEMPEL'S POLY BEST 55551



HEMPEL'S THINNERS 08...

REMARKS: Tools can usually be cleaned with the THINNER prescribed for the product or as described in the product data sheet.

Note: **The information given in the Product Data Sheet is intended for commercial use.**

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Material Safety Data Sheets and follow all local or national safety regulations. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment. Apply only in well ventilated areas.

ISSUED BY: HEMPEL A/S

0808000000C0004
0823000000C0005
0845000000C0009
0851000000C0002
0871000000C0002

*This Product Data Sheet supersedes those previously issued.
For explanations, definitions and scope, see "Explanatory Notes" in the HEMPEL Book.
Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.
The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise.
Product data are subject to change without notice and become void five years from the date of issue.*